

3M Advanced Materials Division

3M™ Fluorosurfactant FC-4430

Introduction

3M™ Fluorosurfactant FC-4430 is a non-ionic polymeric fluorochemical surfactant belonging to a class of coating additives which provide low surface tensions in coating systems best served by fluorochemical surfactants. 3M fluorosurfactant FC-4430 contributes excellent wetting, spreading and leveling properties to a variety of coating systems.

Suggested Applications

3M fluorosurfactant FC-4430 may be used as a flow and leveling agent in various applications including architectural coatings, inks, paints, adhesives, caulks, high solids coatings, water reducible coatings, radiation curable coatings and other industrial coatings.

3M fluorosurfactant FC-4430 can be used in both water and solvent based coating formulations and can provide benefits for dirt pick up resistance and stain resistance in certain applications.

Recommended use level is between 0.05% and 0.3% active surfactant. However, use level can vary depending on the application and concentration of other additives and solvents in the formulation.

Note: All values determined at 77°F (25°C) unless otherwise specified

Typical Physical Properties


(Not for specification purposes)

Properties	Typical Values
Appearance	Clear, yellow viscous liquid
Specific gravity	1.14 g/cc
Flash point (Setaflash closed cup)	>93°C (200°F)
pH (of 1% aqueous solution)	4.5
Viscosity (cP @ 25°C / 77°F)	2,000 - 6,000
Solubility in water	Dispersible in all proportions
Tg	< 0°C
Type	Non-ionic
Composition	90% polymeric fluorochemical actives
	8% non-fluorochemical actives
	2% co-solvent (DPM, toluene)
Freeze/thaw stability	Protect from freezing*

* If 3M fluorosurfactant FC-4430 freezes, warm it to >86°F (>30°C) until fluid. Freezing will not change physical properties or adversely affect performance.

Surface Tension/CMC (in water)

3M fluorosurfactant FC-4430 is very efficient at reducing the surface tension in aqueous coating systems.



Foaming

3M™ Fluorosurfactant FC-4430 shows low tendency to form foam in aqueous systems. This can translate into the ability to use less defoamer and/or a less aggressive defoamer additive in your formulation.

Property	FC-4430
Foam Quality, %	85.58
Foam Stability, minutes (t 1/2 value)	2

Solubility

Solvent	Solvent grams of FC-4430/100 grams of solvent
Butyl cellusolve	>25
Toluene	>35
Methyl ethyl ketone	>25
Dimethylformamide	>25
Isopropyl alcohol	>25
Methanol	>25
Dowanol™ PM	>25
Texanol™	>25
Proglyde™ DMM	>25
N-methyl pyrrolidone	>25
Mineral spirits	<1

3M™ Fluorosurfactant FC-4430 Static Surface Tensions in Water-Borne Resins

Resin	Control	HC Surfactant 1%	FC-4430 0.3%	Competitive FC Surfactant 0.3%	Silicone Surfactant 0.5%
NeoCryl™ A-6099	39.1	29.0	24.3	26.1	27.3
NeoRez™ R-941	43.1	29.8	21.2	24.4	23.8
NeoRez™ R-9621	47.4	33.1	21.2	24.2	22.8
Joncryl® 537	37.4	31.8	19.7	25.6	27.6
Joncryl® 1532	38.4	32.9	21.2	26.9	28.9
Joncryl® 1925	41.0	31.2	19.7	25.4	27.1
Joncryl® 1972	38.9	27.6	22.4	26.3	27.6

Interfacial Surface Tensions

Surfactant	Interfacial Tension Light Phase: Heptane (dynes/cm)			Interfacial Tension Light Phase: Cyclohexane (dynes/cm)		
	200 ppm	0.5%	1.0%	200 ppm	0.5%	1.0%
Control		43.7			51.2	
FC-4430	3.5	2.2		2.5	1.5	
SDS ¹	15.4	6.1	5.8	12.9	5	4.9
SDBS ²	15.9	4.1	3.7	13.5	2.9	2.6
Silicone Dispersant	14.4	10.9	10.5	11.7	8.8	8.8

¹Sodium Dodecyl Sulfate

²Sodium Dodecyl Benzene Sulfonate

Static Surface Tensions in Organic Solvents/Systems

Solvent	Weight % FC-4430			
	0.0	0.1	0.2	0.5
Distilled Water	72	23	21	20
Methyl Alcohol	23	23	23	23
Butyl Cellosolve	28	27	27	27
Butyl Carbitol	30	29	29	29
Methyl Ethyl Ketone	25	24	24	24
Toluene	28	28	28	28
Dimethylformamide	33	33	33	32
Polyethylene Triol LG-56	33	23	22	22
Cycloaliphatic Epoxy Resin	46	35	35	27
Epon™ Resin 828-RS	45	22	19	18

Note: Data not for specification purposes

All values determined at 77°F (25°C) unless otherwise specified

Thermal Stability

The active ingredient in 3M™ Fluorosurfactant FC-4430 exhibits good thermal stability when used in thermal processing applications.

TGA data for FC-4430

This data shows the excellent thermal stability of 3M fluorosurfactant FC-4430 if used in a thermal processing application.

Temperature (°C)	FC-4430 Specified % Weight Loss
195	5%
255	10%
305	50%
330	80%
355	90%
405	95%

(10 mg sample heated at 5°C/minute in air).
Temperatures (°C) at which specified % weight loss occur.

Regulatory Summary

- The PFBS-based surfactants produced by 3M have been reviewed by the U.S. EPA and placed on the TSCA inventory. There is a testing consent order in place which only applies to 3M, not 3M customers. The products are REACH compliant in Europe. The products are available for purchase in China, Korea, New Zealand, the Philippines and on a limited basis in Australia, Canada and Japan.
- PFBS and PFBS-based surfactants are not included in the U.S. EPA's PFAS Final Significant New Use Rule (SNUR) (67 Fed. Reg. 72854).

Packaging

3M fluorosurfactant FC-4430 is currently available in:

- 8 lb. pails
- 40 lb. drums
- 250 lb. drums

Product Safety and Handling

3M fluorosurfactant FC-4430 is intended for use in non-dispersive applications.

3M does not recommend this product for use in applications involving repeated exposure through skin contact, inhalation, or ingestion. It is not intended for food, cosmetic, medical or pharmaceutical usage. Neither 3M nor the U.S. Food and Drug Administration has evaluated or reviewed this product for food, cosmetic, medical or pharmaceutical applications.

It is the user's responsibility to determine whether a coating containing this product is durable and properly cured for the end use. Any used or unused material for disposal should be incinerated in an industrial or commercial facility in the presence of a combustible material. Combustion products will include HF. Facility must be capable of handling halogenated materials. As a disposal alternative, dispose of waste product in a facility permitted to accept chemical waste. For additional disposal information, see the product Safety Data Sheet.

For additional product safety and handling information, please read the product label and Safety Data Sheet before using this product.

3M Resources

To request a sample, place an order or request additional information, please contact your local 3M representative, an authorized 3M distributor or call 1 800 367 8905.

Note: Data not for specification purposes
All values determined at 77°F (25°C)
unless otherwise specified

Warranty, Limited Remedy, and Disclaimer: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. User is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application. User is solely responsible for evaluating third party intellectual property rights and for ensuring that user's use of 3M product does not violate any third party intellectual property rights. Unless a different warranty is specifically stated in the applicable product literature or packaging insert, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OF NON-INFRINGEMENT OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damages arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

Technical Information: Technical information, recommendations, and other statements contained in this document or provided by 3M personnel are based on tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed. Such information is intended for persons with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.



3M Advanced Materials Division

3M Center
St. Paul, MN 55144 USA

Phone 1-800-367-8905
Web www.3M.com/paintsandcoatings

Please recycle. Printed in USA.
© 3M 2016. All rights reserved.
Issued: 11/16 11419HB
98-0212-4160-3 Rev. B

Dowanol and Proglyde are trademarks of The Dow Chemical Company. Texanol is a trademark of Eastman Chemical Company. NeoCryl and NeoRez are trademarks of DSM NeoResins.

Joncryl is a registered trademark of BASF. Epon is a trademark of Resolution Performance Products. 3M and Fluorad are trademarks of 3M Company. Used under license by 3M subsidiaries and affiliates.